

LEXAN™ 6060 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 6060 Film is a co-extruded film with improved scratch resistance and a high gloss surface finish. The film has excellent clarity, high heat resistance and excellent formability. LEXAN 6060 Film also provide good dimensional stability and improved pencil hardness. Masking are available on both sides.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL	METHOD	(0000)				
Tensile Strength @ Yield	ASTM D882	psi	8557	ISO 527	MPa	59
Ultimate	ASTM D882	psi	7687	ISO 527	MPa	53
Tensile Modulus	ASTM D882	psi	333585	ISO 527	MPa	2300
Tensile Elongation at Break (TD/MD)	ASTM D882	%	72/26	ISO 527	%	72/26
Tear Strength						
Initiation	ASTM D1004	g/mil	487		kN/m	188
Propagation	ASTM D1338	g/mil	31		kN/m	12
THERMAL						
Coefficient of Thermal Expansion						
CTE -20~60°C, crossflow	ASTM E831	(x10 ⁵ /°F)	0.29	ISO 11359-2	(x10 ⁵ /°C)	9.9
CTE -20~60°C, inflow	ASTM D831	(x10 [°] /°F)	0.24	ISO 11359-2	(x10 [°] /°C)	8.2
,		(x10 / 1)			(x10 / C)	
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.33	ISO 1183	g/m ³	1.19
Water Absorption, 24 hrs.	ASTM D570	% change	0.59	ISO 62	% change	0.16
Pencil hardness (500g)	ASTM D3363	-	2H		-	2H
Taber Abrasion (100 Cycles)	ASTM D1044	Delta Haze%	25		Delta Haze%	25
Surface Tension	Dyne Pens	Dyne	36/38		Dyne	36/38
(PMMA surface/ PC surface)						
				L L		
OPTICAL Refractive index @ 25 °C	ASTM D542-00					
First surface	ASTM D542-00		1.49			
Second surface			1.58			
Light Transmission	ASTM D1003	%	93	ISO 489		93
Yellowness Index	ASTM D1003 ASTM E313	%	0.55	130 489		0.55
	ASTM E313 ASTM D1003	%	0.55			
Haze		% -	0.2	160 2812		0.2
Gloss over Flat Black @ 20°	ASTM D523-60	-	80	ISO 2813		80
			80			
@ 60°			90			90
 @ 85° (PMMA surface) These are typical properties and a 			100			100

٠ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film and are tested at machine direction unless otherwise noted. Trademark of SABIC.

тм

MANUFACTURING SPECIFICATIONS

 NOMINAL GAUGE RANGES
 MIN./MAX LIMIT OF NOMINAL

 0.007-0.015" (0.178mm-0.381 mm)
 -/+ 5%

CONTACT US:

Middle East and Africa

SABIC Global Headquarters PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet 1 Plastics Avenue Pittsfield, MA 01201 USA Toll-free 1 800 323 3783 T 1 413 448 6655 F (888) 443 2033 E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293678 F +31 (0)164 293272 E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet 2550 Xiupu Road Pudong 201319 Shanghai China T +86 21 2037 8188 F +86 21 2037 8288 E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER"S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER"S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DE SCHIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, services or faign do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates. © 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

⁺Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



www.sabic.com/sfs