

LEXAN™ SG305 SHEET FOR SIGNS

PRODUCT DATASHEET

DESCRIPTION

SABIC range of LEXAN sheet sign grades SG305 offers significant advantages over many other sign materials in terms of design freedom, fire performance and weathering properties. It also combines high impact resistance with optical clarity that provides excellent protection against vandalism, ensuring a positive corporate image. LEXAN SG sheet for Signs is available in clear, bronze, opal white (other colors on request) and has a matte finish on the outside surface for reduced reflection and glare. LEXAN SG305 sheet have proprietary UV protected surfaces giving excellent durability to outdoor weathering.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
IMPACT			
Charpy impact, notched 23°C, 3.0 mm	ISO 179/1eA	kJ/m ²	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	70
THERMAL			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x 10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
ELECTRICAL			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
FIRE RATINGS			
Building & Construction			
Europe	EN13501-1	-	b, s1,d0 (2-6mm)

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.

™ Trademarks of SABIC.

FIRE PERFORMANCE

LEXAN SG sheet has good fire behavior characteristics. LEXAN sheet does not contribute significantly to the spread of fire or to the generation of toxic gases. For details please contact your local sales office.

UV PROTECTION

With a proprietary UV resistant surface treatment on both sides LEXAN SG sheets with stand prolonged exposure to harsh sunlight. The superior UV protected surface treatment is not affected by forming and fabricating, and LEXAN SG sheets are therefore backed by a 10 years warranty†) against yellowing, loss of light transmission and breakage. †) see warranty for details.

CHEMICAL RESISTANCE

Taking into account the complexity of chemical compatibility, all chemicals which come into contact with LEXAN sheet should be tested. For sign products the most common materials are adhesives, paints, inks, vinyl films and cleaning. Consult our Technical Service Centre in the case of doubt about the chemical compatibility of a product which is not mentioned in one of the tables.

PRODUCT AVAILABILITY

LEXAN SG sheet is available on economical spools as well as sheet, making it easy to cut non standard sizes.

SHEET AVAILABILITY

Gauges:	Size (mm)	Standard colors
2, 3, 4, 5, 6	2050 x 3050	Clear 112, other colors are upon request.

SPOOL AVAILABILITY

Gauge:
2+3 mm
Only available in full web size 2120 mm
Production: Italy

CONTACT US:

SABIC CORPORATE HQ
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS
SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE
SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 292272
E ff.info@sabic.com

PACIFIC
SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.
© Copyright 2021 All rights reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

