

LEXAN™ CLINIWALL™ C6200 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ CLINIWALL™ sheet is a non-chlorinated and non-brominated opaque sheet, available in standard and custom colours. In addition to good flammability and smoke performance, it offers excellent mechanical properties like impact, stain, blood and urine resistant combined with ease of processing, making it an excellent candidate for a wide range of applications in industries such interior wall cladding and sandwich panel.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.20
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Scratch resistance	Pensile Hardness	9H	No scratches
Flexural Strength (2mm/min)	ISO 178	MPa	90
Linear thermal expansion, 23-55°C	ISO 11359-2	mm	7x10 ⁻⁵ 1/°C
IMPACT			
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	70
THERMAL			
Vicat softening temperature, B/120	ISO 306	°C	145
FIRE RATINGS			
Building & Construction			
Europe	EN13501-1	-	B,s1,d0

- ◆ These property values have been derived from resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Functional Forms representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection-molded samples. All samples are prepared according ISO 294.

™ Trademark of SABIC.

PROCESSING

LEXAN™ CLINIWALL™ sheet is suitable for cold line bending and can be mounted on a wall with a simple glue solution. For details we refer to our processing guide for C6200 sheet.

LEXAN CLINIWALL sheet is suitable for thermoforming. To reach optimal results the materials needs to be heated with sandwich type heating systems to reach uniform heat uptake. Pre-drying of this material is necessary. Pre drying at 100°C for 2 hours /mm thickness

LEXAN CLINIWALL sheet has a processing window between 160 and 200°C. When forming, a draft angle of 3 degrees should be allowed. Post mould shrinkage is dependent on tool temperature and environmental circumstances, but will typically be in the range of 0.5-0.9%.

PRODUCT AVAILABILITY

PRODUCT CODE:	LEXAN CLINIWALL C6200 sheet
TEXTURES:	Polished/Suede (C6206), Polished/Silk Math (C6205) on request with protective masking
COLORS:	WH6G057 (White), BR8G038 (Beige), GY8G179 (Light grey), GN6G033 (Mint green), BL8G009 (Light blue), BL1G038 (Dark blue), GY1G140 (Dark grey), GY7G160 (Medium grey), 86183 (Off white)
SIZES:	C6205: Gauges 1.2 and 1.5mm, W – L = 1300 – 3050mm C6206: Gauges 1.5 and 1.7mm, W – L = 1300 – 3050mm

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 293272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.
© Copyright 2021. All rights reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



LEXAN is a trademark of SABIC