

LEXAN™ ULG1003 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ ULG1003 sheet is a transparent lamination grade offering excellent optical properties for lamination with glass in mainly symmetrical security glazing panels. The product is unique in the market in terms of visual defects and low optical distortion. Can be specified to match specific levels of threat and has an excellent optical clarity.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
IMPACT			
Charpy impact, notched 23°C, 3.0 mm	ISO 179/1eA	kJ/m ²	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	70
THERMAL			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
ELECTRICAL			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
FIRE RATINGS			
Aircraft			
Vertical burn, 12 s	FAR 25.583(a)+App.F	-	Pass (3-6mm)

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.

™ Trademarks of SABIC.

CHEMICAL RESISTANCE

Although LEXAN™ ULG1003 sheet is resistant to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels, we strongly recommend testing of applications where the product will come into contact with these or other aggressive chemicals. For asymmetrical configurations where the LEXAN surface will not be bonded with glass, we advise to apply our 1-side hard coated product LEXAN MARGARD HLG5 and HLG3 sheets.

OPTICAL PROPERTIES

The optical qualities of LEXAN ULG1003 sheets are the result of constant research in order to provide the best values. LEXAN ULG1003 sheets in 2-12 mm thickness are passing a diopter value of 0.06 points according DIN 52305-A-AZ which specifies optical requirements for glazing in vehicles. During the optical control phase, LEXAN ULG1003 sheets are examined against a special background, called image magnification, for proper identification of optical imperfections. Our internal manufacturing specifications are under constant supervision of our ISO 9002 approved Quality Management department.

PRODUCT AVAILABILITY

Product code:	ULG1003 sheet
Standard size:	2050 x 3050 mm [‡]
Thicknesses:	2,3,4,5,6,8,9.5, 12 and 15 mm
Standard color:	112 (clear) [‡]

[‡]) Different colors and dimensions can be made available by prior arrangement for ULG1003. Such arrangements may affect prices and/or conditions of sale.

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 293272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.
© Copyright 2021. All rights reserved.

[†] Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

