

LEXANTM 9604/96054 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXANTM 9604/ 96054 sheet offers all the benefits of standard, transparent polycarbonate sheet - excellent impact resistance, good stiffness and strength, high optical quality, excellent formability, relatively light weight - but it has significantly better flammability characteristics, making it suitable for a wide variety of applications in the transportation, electrical and electronic industries.

9604 (Polish / Polish) 96054 (Velvet / Polish)

TYPICAL PROPERTY VALUES◆

PROPERTY	TEST METHOD	UNITS	VALUE
Physical			
Specific Gravity	ASTM D792	g/m³	1.26
Water Absorption, Equilibrium, 24 Hrs	ASTM D570	%	0.20
Light Transmission (avg.), .125" thickness	ASTM D1003	%	85
Mechanical			
Tensile Strength	ASTM D638	ρsi	9,500
Ultimate			9,000
Elongation	ASTM D638	%	95
Tensile Modulus	ASTM D638	ρsi	235,000
Flexural Strength	ASTM D790	ρsi	13,500
Flexural Modulus	ASTM D790	ρsi	370,000
Compressive Strength	ASTM D695	ρsi	12,500
Dynatup Impact Strength,			
1/2" dia. dart, (gauge dependant)***, @ 73°F	ASTM D3783	ft-lbs	50
Gardner Impact Strength,			
round tup (gauge dependent)***, @ 73°F	ASTM D3029	in-lbs	>320
Izod Impact Strength, (gauge dependant)***	ASTM D256A	ft-lbs/in	
Notched @ 73°F			2,4
Unnotched @ 73°F			NB
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75×10^{-5}
Heat Deflection Temperature	ASTM D648	°F	
@ 264 psi			280
Flammability			
UL Flammability**	UL 94	-	V-0 (90 mils and above)
			V-2 (34–89 mils)
FAA Flammability @ 40 to 125 mils	FAR 25.853	-	Passes A&B
ATS 1000 (a) 40 to 125 mils	_	-	Pass

[◆] These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.

UL File Number: E121562

[™] Trademarks of SABIC

^{**} This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

^{***} Reported values based on .125" gauge thickness.

CONTACT US:

MIDDLE EAST AND AFRICA

SABIC Global Headquarters PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 E info@sabic.com

AMERICAS

Functional Forms 2500 City West Boulevard Suite 100 Houston, TX 77042 USA Inside sales: Toll-free (800) 323 3783 E spinside.sales@sabic.com

EUROPE

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
E ff.info@sabic.com

PACIFIC

Functional Forms 2550 Xiupu Road Pudong 201319 Shanghai China T +86 20 2866 6168 E ff.info@sabic.com



DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

 $\hbox{@ 2023 Saudi Basic Industries Corporation (SABIC).}$ All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.