



# LEXAN™ COGC08 Corrugated Sheet

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ COGC08 Corrugated Sheet is a Greca profile panel offering high impact strength and excellent light transmission. This product is an excellent candidate for greenhouse coverings. LEXAN Corrugated Sheet offers additional features of long term weathering (UV protection), excellent impact resistance, and a ten year limited written warranty for weathering and a three year limited written warranty against hailstone breakage. LEXAN Corrugated Sheet has one side UV protected and the other side has a factory applied coating (Drip Guard) to help prevent plant disease caused by dripping condensation.

### TYPICAL PROPERTY VALUES ◆

PROPERTY	TEST METHOD	UNITS	VALUE
<b>Physical</b>			
Specific Gravity (color dependent)	ASTM D792A	-	1.20
Density	ISO 1183	g/cm <sup>3</sup>	1.2
Light Transmission	ASTM D1003	%	89 (Clear)
Corrugation Height	-	Mm	76
Corrugation Pitch	-	Mm	16
<b>Mechanical</b>			
Tensile Strength	ASTM D638	psi	9,500
	ISO 527	MPa	60
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	Psi	340,000
	ISO 527	MPa	2300
Gardner Impact Strength (Gauge Dependent)	SABIC Method	In-lbs	>240
		J	24
<b>Thermal</b>			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x10 <sup>-5</sup>
	DIN 53752	1/°C	7x10 <sup>-5</sup>
<b>Flammability</b>			
Flammability Burn Class	ASTM D635		CC1

◆ These property values have been derived from LEXAN resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.‡ 5-lb steel ball dropped from a height of 40 feet

™ Trademarks of SABIC.

## PRODUCT AVAILABILITY – GREGA PROFILE

Product Code	LEXAN COGC08 Corrugated Sheet (Made in Campinas, Brazil)
Profile	Greca 76 mm x 16 mm
Gauge	0.033" / 0.84 mm
Sheet Weight	0.242 lbs/SFT
Standard Width	51" / 1295.4mm
Standard Length	464.57" / 11,800 mm
Minimum Length	96" / 2439 mm
Colors	Clear=112 Opal=82253 Bronze=515055 Diffused=SOFTL
Light Transmission	Clear=89% Opal=50% Bronze=25% SOFTL 84% (Diffusion / Haze 100%)
Masking	None
UV Tape	"LEXAN Corrugated Sheet", applied to UV protected side



## CONTACT US

### SABIC CORPORATE HQ

PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
E info@sabic.com

### AMERICAS

SABIC  
Functional Forms  
2500 CityWest Boulevard  
Suite 100  
Houston, TX 77042  
USA  
Toll-free (800) 323 3783  
E spinside.sales@sabic.com

### EUROPE

SABIC  
Functional Forms  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293684  
E ff.info@sabic.com

### PACIFIC

SABIC  
Functional Forms  
2550 Xiupu Road Pudong  
201319 Shanghai  
China  
T +86 20 2866 6168  
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with <sup>TM</sup> are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.  
© 2022 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.