

# LEXAN<sup>TM</sup> F6000 SHEET

## PRODUCT DATASHEET

## **DESCRIPTION**

LEXAN<sup>TM</sup> F6000 sheet is a flame retardant opaque polycarbonate sheet range available in standard and custom colors. In addition to good flammability performance, it offers excellent impact resistance, good stiffness and strength and ease of processing, making it suitable for a wide variety of applications in industries such as electrical/electronics and transportation (e.g. aircraft, rail).

## TYPICAL PROPERTY VALUES◆

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm³	1.21
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
IMPACT			
Charpy impact, notched, 3.0 mm	ISO 179/1eA	kJ/m²	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m²	70
THERMAL			
Vicat softening temperature, B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7×10 <sup>-5</sup>
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
ELECTRICAL			
Volume resistivity	IEC 60093	Ohm.cm	>10 <sup>15</sup>
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
OPTICAL			
Light transmission 3 mm	ASTM-D1003	%	n/a

PROPERTY	TEST METHOD	UNITS	VALUE
FIRE RATINGS			
Aircraft			
Vertical burn, 60 s	FAR 25.853(a)+App.F	-	Pass (1-6mm)
Smoke density	ABD0031	-	Pass, Ds(4min)<150 (1-6mm)
Smoke toxicity	ABD0031,BSS 7239	-	Pass (1-6mm)
Rail			
France	NF P 92-501	-	M2 (2mm)
France	NF F 16-101	-	F2 (2mm)
UK	BS 6853	-	Ao=0.125
Germany	DIN 5510-2		S4/ST2/SR2, FED<1 (1mm) S4/ST2/SR1, FED<1 (1.5-4mm)
Italy	UNI CEI 11170-3	-	Class 1B (1-3mm)
Electrical			
Limited Oxygen Index	ISO 4589-2	%	35
UL listing - <u>E45329</u>			

Typical values only. Variations within normal tolerances are possible for the various textures.

#### **PROCESSING**

LEXAN<sup>TM</sup> F6000 sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. LEXAN F6000 sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least  $3^{\circ}$  should be allowed, and post mold shrinkage of 0.3 - 0.8% taken into account, depending on mold temperature.

## PRE-DRYING

It is important to ensure that Lexan F6000 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying of 2 hours/mm thickness.

## **ASSEMBLING**

Parts made from LEXAN F6000 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC, Film & Sheet representative for advice on specific applications.

## **PAINTING**

LEXAN F6000 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available upon request.

## CHEMICAL RESISTANCE

LEXAN F6000 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the LEXAN F6000 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance.

<sup>™</sup> Trademark of SABIC.

## PRODUCT AVAILABILITY

Product code: LEXAN F6000

**Textures:** Polished/Suede (F6006)

See product availability guide for available gauges, sizes, and colors.

#### **SAFETY**

The processing guidance given in this documentation is given in good faith and the trust that in all cases you wear the correct Personal Protective Equipment (PPE), e.g. helmet, proper gloves, safety goggles etc. to safely fabricate, e.g. (but not limited to) sawing, cutting, forming our sheets and films. In all cases you should follow local and national regulations around the wear of PPE's prescribed or mandatory to perform these tasks in a safely manor.

## **CONTACT US:**

#### SABIC CORPORATE HQ

PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com

#### **AMERICAS**

SABIC Functional Forms 2500 City West Boulevard Suite 100 Houston, TX 77042 USA Toll-free (800) 323 3783

USA Toll-free (800) 323 3783 F (888) 443 2033 E spinside.sales@sabic.com EUROPE

SABIC Functional Forms Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293684 F +31 (0)164 292272 E ff.info@sabic.com

## PACIFIC

SABIC Functional Forms 1266 Nanjing Road (A) 16<sup>th</sup> Floor, Plaza 66 200040 Shanghai China T +86 21 3222 4500 F +86 21 6289 8998 E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with  $^{\rm TM}$  are trademarks of SABIC or affiliates.  $^{\rm C}$  Copyright 2021. All rights reserved.

<sup>†</sup> Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

