

LEXAN™ HPxxW FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ HPxxW graphic film is a high-performance coated film offering very good chemical/abrasion resistance, plus very good UV resistance. These performance capabilities, along with LEXAN film's ease of processing, make HPxxW film a good choice for outdoor graphic applications such as: Warning Labels, Outdoor Menu Boards, Gasoline Pumps, Outdoor Lenses, and Marine Graphics.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM (ISO) TEST METHOD	UNITS USCS (SI)	HP12W	HP92W
MECHANICAL				
Tensile Strength @ Yield	ASTM D882 (ISO 527)	psi (MPa)	8800 (60)	8800 (60)
Ultimate	ASTM D882 (ISO 527)	psi (MPa)	9000 (62)	9000 (62)
Tear Strength				
Initiation	ASTM D1004	lb/mil (kN/m)	1.51 (264)	1.51 (264)
Propagation	ASTM D1922	g/mil (kN/m)	40 (14)	40 (14)
THERMAL				
Vicat Softening Temperature, B	ASTM 1525	°F (°C)	320 (160)	320 (160)
Heat Deflection Temp. by TMA at 1.8 Mpa	ISO 75 Modified	°F (°C)	290 (145)	290 (145)
Shrinkage at 302°F (150°C)	ASTM D1204	%	1.40%	1.40%
PHYSICAL				
Density	ASTM D792 (ISO 1183)	slug/ft ³ (kg/m ³)	2.3 (1200)	2.3 (1200)
Surface Energy (1st surface / 2 nd surface)	ASTM D5946-01	-	NA/34	NA/34
Surface Tension (1st surface / 2 nd surface)	Dyne Pens	Dyne	NA/38-40	NA/38-40
Pencil Hardness (coated surface)	ASTM D3363	-	HB-F	HB-F
Taber Abrasion	ASTM D1044	delta Haze	<1	<2
OPTICAL				
Light Transmission	ASTM D1003	%	90	92
Yellowness Index	ASTM D1925	%	1.3	0.7
Haze	ASTM D1003	%	56	0.5
Gloss over Flat Black min/max @ 60	ASTM D523-60 (ISO 2813)	-	12	92
UV% Transmission at 380 nm	UV/Visual Spectroscopy	%	14	39

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.
Reported Values are based on 0.010" (0.250 mm) Thickness unless otherwise noted.

™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	HP12W	MIN./MAX LIMIT OF NOMINAL
0.007" (0.175mm)		- 10%/ +24%
0.010" (0.250 mm)		- 5%/+20%
0.015" (0.375 mm)		- 5%/+9%
0.020" (0.500 mm)		-3%/+6%
0.025" (0.625 mm)		-3%/+10%


NOMINAL GAUGE RANGES	HP92W	MIN./MAX LIMIT OF NOMINAL
0.007" (0.175mm)		- 10%/ +24%
0.010" (0.250 mm)		- 5%/+20%
0.015" (0.375 mm)		- 5%/+12 %
0.020" (0.500 mm)		- 5%/+10 %
.030" (0.762 mm)		- 5%/+5 %

UV RESISTANCE

LEXAN HPxxW film utilizes a proprietary coating technology developed by SABIC. This special coating resists yellowing and hazing – no matter how bright the sun. With a yellowness index of less than 3.0 at 1000 hours of QUV testing and less than 2.0 at 1000 hours of Xenon Arc testing, LEXAN HPxxW film is a natural choice for demanding outdoor applications.

MASKING

The standard masking on HP film is not designed to have UV radiation (for curing) passed through it. If this is required, alternate masking is available. Please contact your sales representative for more details.



CHEMICAL AND ABRASION RESISTANCE

Along with very good UV resistance, LEXAN HPxxW film also has chemical and abrasion resistance comparable with the original HPS series of films.

TABER ABRASION RESISTANCE (ASTM D1044)

LEXAN HPxxW GRAPHIC FILM

CONDITION	UNITS	HP12W	HP92W
CS10F WHEEL, 500 GRAMS			
25	Change in % Haze	0.4	2
50	Change in % Haze	0.6	2.9
100	Change in % Haze	2	6.6
200	Change in % Haze	6.7	13.8

CHEMICAL RESISTANCE

CHEMICAL	RESULTS†
One Hour Continuous Surface Contact at 73° F	
Acetone	Failed
MEK	Failed
Toluene	Failed
Methylene Chloride	Failed
Isopropyl Alcohol	Passed
Cyclohexanone	Passed
Ethyl Acetate	Failed
Xylene	Passed
40% NaOH	Passed
Concentrated HCl	Passed
Gasoline (Regular)	Passed
Gasoline (Unleaded)	Passed
Butyl Cellosolve	Passed

24 hour continuous Surface Contact at 120°F	
Coffee	Passed
Top Job [‡]	Passed
Fantastik ^{###}	Passed
Formula 409 [#]	Passed
Windex w/ Ammonia D ^{####}	Passed
Wisk [¶]	Passed
Downy [#]	Passed
Spray N Wash ^{##}	Passed
Clorox [*]	Passed
Mustard	Passed
Mr. Clean [#]	Passed
Ketchup	Passed
Tea	Passed
Tomato Juice	Passed
Lemon Juice	Passed
Grape Juice	Passed
Vinegar	Passed
Milk	Passed

† Failure constitutes any of the following: non-removable stain or cloudiness, blistering, delamination, or cracking of the coating or failure to pass crosshatch tape adhesion.

¶ Wisk is a registered trademark of Lever Brothers Company

Formula 409 and Clorox are registered trademarks of the Clorox Company

‡ Top Job, Downy, and Mr. Clean are registered trademarks of Procter & Gamble

Fantastik and Spray 'N Wash are registered trademarks of Texize, Division of Norton Norwich Products, Inc.

Windex w/Ammonia D is a registered trademark of Drackett Products Company

SAFETY

The processing guidance given in this documentation is given in good faith and the trust that in all cases you wear the correct Personal Protective Equipment (PPE), e.g. helmet, proper gloves, safety goggles etc. to safely fabricate, e.g. (but not limited to) sawing, cutting, forming our sheets and films. In all cases you should follow local and national regulations around the wear of PPE's prescribed or mandatory to perform these tasks in a safely manor.

CONTACT US:

MIDDLE EAST AND AFRICA

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Inside sales:
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 292272
E ff.info@sabic.com

ASIA PACIFIC

Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com



DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2021 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs