

VALOX™ FR1 FILM

PRODUCT DATASHEET

DESCRIPTION

VALOX™ FR-1 film is an impact modified flame retardant Polybutylene Terephthalate/Polycarbonate (PBT/PC) alloy film offering UL94 VTM-0 performance down to 130 microns and good temperature performance. VALOX™ FR-1 film's outstanding chemical resistance, dielectric strength and ease of fabrication (ie: thermoforming, embossing, clean-edge die-cutting, folding and bending) makes it very suitable for a wide range of electrical, electronic and medical applications.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	7200	ISO 527	MPa	49.7
Ultimate	ASTM D882	psi	6000	ISO 527	MPa	41.1
Tensile Modulus	ASTM D882	psi	277000	ISO 527	MPa	1910
Tensile Elongation at Break	ASTM D882	%	57	ISO 527	%	57
Gardner Impact Strength at 0.03" (0.75 mm)	ASTM D3029	ft-lb	7	ISO 6603-1	J	10
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.46		kN/m	255
Propagation	ASTM D1922	g/mil	55		kN/m	20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.007" (0.175 mm)	ASTM D2176-69	double folds	2000			
0.020" (0.625 mm)	ASTM D2176-69	double folds	83			
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.17
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.1	ISO 11359	(x10 ⁻⁵ /°C)	5.7
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.31
Glass Transition Temperature	ASTM D3417 / D3418	°F	183	ISO 11357	°C	84
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	346		°C	174
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	174	ISO 75 Modified	°C	79
Shrinkage at 302°F (150°C)	ASTM D1204	%	0.40		%	0.40
Brittleness Temperature	ASTM D746	°F	-211		°C	-135
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.6	ISO 1183	kg/m ³	1340
Water Absorption, 24 hrs.	ASTM D570	% change	0.48	ISO 62	% change	0.48
Surface Energy(1 st surface/ 2 nd surface)	ASTM D5946-01	-	36/35			
Surface Tension(1 st surface/ 2 nd surface)	Dyne Pens	Dyne	>44/34-36			
Pencil Hardness	ASTM D3363	-	2b-b			

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
OPTICAL						
Light Transmission	ASTM D1003	%	15			
Yellowness Index	ASTM D1925	%	49			
Haze	ASTM D1003	%	103			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	5	ISO 2813		5
ELECTRICAL						
Dielectric Strength in oil, short time @ 72°F (23°C), 10 mils (0.25mm)	ASTM D 149-97a Method A	kV/mil	1.09	IEC 60243	kV/mm	43
Dielectric Constant @ 60 Hz	ASTM D150	-	3.3	IEC 60250	-	3.3
@1,000,000 Hz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor @ 60 Hz	ASTM D150	-	0.0015	IEC 60250	-	0.0015
@1,000,000 Hz	ASTM D150	-	0.01	IEC 60250	-	0.01
Volume Resistivity	ASTM D257	Ω-cm	1E+17	IEC 60093	Ω-cm	1E+17
Surface Resistivity	ASTM D257	Ω/square	1E+16	IEC 60093	Ω/square	1E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	21			

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010”) thickness film unless otherwise noted.

™ Trademark of SABIC.

GLOSS BY GAUGE: (ASTM D 523-85)

	GAUGE	ANGLE		MATTE
FR1	.003" (0.075mm)	85°	Minimum	0.1
			Maximum	25
	0.006 - 0.030" (0.150 - 0.750mm)	85°	Minimum	0.1
			Maximum	17

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.003 - 0.010" (0.075 mm-0.250 mm)	-/+10%
0.015 - 0.030" (0.375 - 0.750mm)	-/+5%

Color Code:

Black Color – BK1066 (BK)

Natural Color – 1001 (NC)

UL File Number: [E121562](#), [E207780](#)

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Inside sales:
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 292272
E ff.info@sabic.com

ASIA PACIFIC

Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with TM are trademarks of SABIC or affiliates.
© Copyright 2022. All rights reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

